

Iroko

Family Name: Moraceae

Latin Name: Chlorophora Excelsa

Origin: Africa - Tropical

Strength Class: D40

Weight: Approx 660 kg/m³

Durability: Very Durable

Description: Golden Yellow in colour which darkens over time. Dense timber, with an interlocked grain. Has a medium to coarse texture with open pores.

Mechanical Properties: Dries well and fairly quickly, with only a slight tendency of splitting. Moderate steam bending. Glues and finishes well.

Main Uses:	Marine Work	Cabinet Work
	Piling	Cladding
	Boat Building	Decking
	Furniture	Flooring
	Joinery	